

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
19 July 2001 (19.07.2001)

PCT

(10) International Publication Number
WO 01/51731 A1

(51) International Patent Classification⁷: E04C 5/07

(21) International Application Number: PCT/US01/00561

(22) International Filing Date: 8 January 2001 (08.01.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/175,894 13 January 2000 (13.01.2000) US

(71) Applicant: **THE DOW CHEMICAL COMPANY**
[US/US]; 2030 Dow Center, Midland, MI 48674 (US).

(72) Inventors: **EDWARDS, Christopher, Michael**;
2613 Hearstone Circle, Midland, MI 48642 (US).
D'HOOGE, Edward, L.; Steensedijk 56, NL-4561 GN
Hulst (NL).

(74) Agent: **WILLIS, Reid, S.**; Intellectual Property, P.O. Box
1967, Midland, MI 48641-1967 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.


(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: SMALL CROSS-SECTION COMPOSITES OF LONGITUDINALLY ORIENTED FIBERS AND A THERMOPLASTIC RESIN AS CONCRETE REINFORCEMENT



(57) Abstract: Small cross-section composites are used as reinforcements for concrete. The composites include longitudinally oriented fibers embedded in a depolymerizable and repolymerizable thermoplastic matrix. The composites are mixed into the wet concrete and poured with the concrete to form a reinforced concrete structure.

WO 01/51731 A1

BEST AVAILABLE COPY

SMALL CROSS-SECTION COMPOSITES OF LONGITUDINALLY
ORIENTED FIBERS AND A THERMOPLASTIC RESIN AS CONCRETE
REINFORCEMENT

5 STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR
DEVELOPMENT

The research and development leading to the subject matter disclosed herein was
not federally sponsored.

10

This invention relates to reinforcing materials for concrete and concrete structures
so reinforced.

Concrete is one of the most common building materials. It is used in a wide
variety of structures such as bridges, walls, floors, building supports, roadways, and
15 runways among many others.

15

For several reasons, concrete structures are usually made with some sort of
reinforcement. Concrete is often prone to cracking as the structure is weathered or
subjected to bending loads and impact. This is mainly due to the poor tensile properties
of the concrete. Reinforcing materials are commonly used to improve the tensile
20 properties of concrete structures. In addition, concrete is applied wet and in some
instances must hold its position shape (against, e.g. the force of gravity) until it hardens.
Sometimes reinforcing materials are added to the concrete to help hold the mass
together and in position until it sets.

20

Concrete reinforcements come in several types. Reinforcing bars are common.
25 These are typically steel but are sometimes a thermoset/fiber composite. A second type
of reinforcement is an overwrap. The overwrap is commonly a thermoset/fiber
composite that is applied to the outside of a structure. Overwraps of this sort are often
used to shore up a cracked or damaged structure, or to strengthen structures so they
become more resistant to natural phenomena such as hurricanes, tornadoes and
30 earthquakes. Overwraps are not limited to concrete structures—they can be applied to
structures of many types of construction, such as brick, stone, and frame constructions.

30

A third type of concrete reinforcement is fibers that are embedded in the concrete. The fibers used in this application are usually steel or polypropylene. These fibers are short, commonly of the order of 12-50 mm in length, and typically have a diameter of around 0.1-1 mm. The fibers are mixed into the wet concrete. When the concrete is poured, the fibers become randomly oriented in the concrete, forming a "fuzzy" matrix that helps prevent cracking or crack propagation. This matrix also helps hold the wet concrete together until it can harden.

The common steel and polypropylene fibers each have significant limitations. Steel fibers are very strong and stiff, but they are difficult to handle and apply. They are prone to corrosion when exposed to water and salts. Polypropylene fibers do not corrode, but are undesirably ductile and not as strong as desired. Further, with all fibers but especially strong stiff fibers such as steel, it is relatively difficult to generate the full strength of the fibers since they do not bond adequately to the concrete so that when a load is applied, they tend to pull out below their ultimate failure strength.

Glass fibers would have an excellent combination of stiffness, strength and resistance to corrosion, but they are too brittle for this application. The process of mixing glass fibers into the concrete and pouring the concrete breaks the fibers up into short lengths that do not provide much reinforcement. In addition, glass fibers are not chemically stable in the alkaline environment of concrete.

In order to overcome the deficiencies of glass fibers, it has been attempted to provide them with a polymeric coating. The polymeric coating would be expected to reduce the friability of the glass fibers as well as protect them from the alkalinity of the concrete. However, it is difficult and expensive to provide glass fibers with a suitably thin coating that also completely covers the fibers.

Thus, it would be desirable to provide an improved method by which reinforcement can be provided to concrete, which provides high strength and stiffness combined with ease of handling, no corrosion and excellent mechanical and/or chemical bonding into the concrete.

In one aspect, this invention is a composite adapted for use in a concrete structure, the composite comprising a plurality of longitudinally oriented fibers embedded in a matrix of a depolymerizable and repolymerizable thermoplastic resin,

said composite having a longest cross-sectional dimension of not more than about 5 mm and an aspect ratio of at least 10.

In a second aspect, this invention is a concrete structure reinforced with up to 10 volume-percent of a small cross-section composite, said small cross-section composite comprising a plurality of longitudinally oriented reinforcing fibers embedded in a matrix of a depolymerizable and repolymerizable thermoplastic resin, said small cross-section composite having a longest cross-sectional dimension of not more than about 5 mm and an aspect ratio of at least 10.

In a third aspect, this invention is a method of making a reinforced concrete structure, comprising the steps of (a) forming a wet concrete mix containing a mortar or cement, a particulate filler and up to 10 volume-percent of a small cross-section composite, said small cross-section composite comprising a plurality of longitudinally oriented fibers embedded in a matrix of a depolymerizable and repolymerizable thermoplastic resin, said small cross-section composite having a longest cross-sectional dimension of not more than about 5 mm and an aspect ratio of at least 10, (b) shaping the concrete and (c) permitting the concrete to cure.

Figures 1 and 2 are isometric views of embodiments of the invention.

The small cross-section, composite of this invention comprises a composite of longitudinally oriented fibers embedded in a matrix of a thermoplastic resin. It is conveniently made in a pultrusion process as described in U. S. Patent No. 5,891,560 to Edwards et al. By "small cross-section", it is meant that the small cross-section composite has a longest cross-sectional dimension of no greater than about 5 mm.

The small cross-section composite advantageously has a longest cross-sectional dimension of up to 5 mm, preferably of up to about 2.5 mm. It has an aspect ratio of at least 10, preferably at least 25, more preferably at least 40. The small cross-section composite can have any convenient cross-sectional shape, including circular, elliptical, oval, semicircular, rectangular, square, or any other regular or irregular polygon shape.

A typical small cross-section composite has a width of from about 0.2 to about 5 mm, preferably about 0.5 to about 2 mm, and a thickness of 0.1 to about 1 mm. A

suitable length is from about 10 to about 100 mm, preferably about 15 to about 75, more preferably 25 to about 60 mm.

The small cross-section composite preferably has some curvature or bending that provides sites for interlocking with the cured concrete. The curvature can take the form, for example, of a sinusoidal curve or wave throughout the length of the small cross-section composite, or can take the form of one or more, preferably at least two, localized curves or bends. Figures 1 and 2 illustrate exemplary ways how this curvature or bending can appear. In Figure 1, small cross-section composite 1 is generally flat but has sinusoidal curve 6 running throughout its length. In Figure 2, small cross-section composite 4 has terminal curves 2 and 3, forming terminal sections 7 and 8 that are angled with respect to the plane of the main portion 9 of the small cross-section composite. Another way to provide for mechanical keying into the concrete is to form a spiraled composite having any non-circular cross-section. This effect can be obtained by pultruding any cross-sectional shape except a circle, and either twisting the pultruded mass after it exits the die or rotating the die during the pultrusion process.

The fiber can be any strong, stiff fiber that is capable of being processed into a composite through a pultrusion process and bonds well to the thermoplastic resin. Suitable fibers are well known and are commercially available. Glass, other ceramics such as SiC, boron, B₄C, Al₂O₃, MgO and Si₃N₄, carbon, metal or high melting polymeric (such as aramid) fibers are suitable. Mixtures of different types of fibers can be used. Moreover, fibers of different types can be layered or interwoven within the composite in order to optimize certain desired properties. For example, glass fibers can be used in the interior regions of the small cross-section composite and more expensive fibers such as carbon fibers used in the exterior regions. This permits one to obtain the benefits of the high stiffness of the carbon fibers while reducing the overall fiber cost. In addition, the exterior carbon fibers provide additional protection of the glass fibers from the alkaline environment in the cement.

Glass is a preferred fiber due to its low cost, high strength and good stiffness.

Suitable fibers are well known and commercially available. Fibers having diameters in the range of about 10 to 50 microns, preferably about 15-25 microns, are particularly suitable.

The fibers are longitudinally oriented in the small cross-section composite. By "longitudinally oriented", it is meant that the fibers extend essentially continuously throughout the entire length of the small cross-section composite, and are aligned in the direction of pultrusion.

5 As it is the fibers that mainly provide the desired reinforcing properties, the fiber content of the small cross-section composite is preferably as high as can conveniently be made. The upper limit on fiber content is limited only by the ability of the thermoplastic resin to wet out the fibers and adhere them together to form an integral composite without significant void spaces. The fibers advantageously constitute
10 at least 30 volume-percent of the small cross-section composite, preferably at least 50 volume-percent and more preferably at least 65 volume-percent.

The depolymerizable and repolymerizable thermoplastic resin (DRTP) can be any that can be adapted for use in a pultrusion process to form the composite and which does not undesirably react with the fibers. However, the DRTP resin preferably has additional
15 characteristics. The DRTP resin preferably is a rigid polymer having a T_g of not less than 50°C. In addition, the DRTP resin preferably forms a low viscosity melt during the pultrusion process, so as to facilitate wetting out the fibers. The DRTP resin preferably does not react with concrete in an undesirable way and is substantially inert to (i.e., does not react with, absorb, dissolve or significantly swell when exposed to) water and
20 common salts.

A particularly suitable DRTP is a rigid thermoplastic polyurethane or polyurea (both referred to herein as "TPUs"). TPUs have the property of partially depolymerizing when heated due in part to the presence of residual polymerization catalyst. The catalyst is typically hydrolytically- and thermally stable and is "live" in the sense that it is not
25 inactivated once the TPU has been polymerized. This depolymerization allows the TPU to exhibit a particularly low melt viscosity, which enhances wet-out of the fibers. Upon cooling, the polyurethane repolymerizes to again form a high molecular weight polymer.

In addition, TPUs tend to form particularly strong adhesive bonds to concrete.

Suitable thermoplastic polyurethanes are described, for example, in U. S. Patent
30 No. 4,376,834 to Goldwasser et al. Composites that can be adapted for use in the invention and which are made using such rigid TPUs are described in U. S. Patent No. 5,891,560 to Edwards et al.

The composites described in U. S. Patent No. 5,891,560 include a continuous phase which is advantageously a polyurethane or polyurea (or corresponding thiourethane or thiourea) impregnated with at least 30 percent by volume of fibers that extend through the length of the composite. The general pultrusion process described in U. S. Patent No. 5,891,560 includes the steps of pulling a fiber bundle through a preheat station, a fiber pretension unit, an impregnation unit, a consolidation unit that includes a die which shapes the composite to its finished shape, and a cooling die. The pulling is advantageously accomplished using a haul off apparatus, such as a caterpillar-type haul off machine. Additional shaping or post-forming processes can be added as needed.

As described in U. S. Patent No. 5,891,560, the preferred continuous phase polymer is a thermoplastic polyurethane or polyurea made by reacting approximately stoichiometric amounts of (a) a polyisocyanate that preferably has two isocyanate groups per molecule, (b) a chain extender, and optionally (c) a high equivalent weight (i.e., above 700 to about 4000 eq. weight) material containing two or more isocyanate-reactive groups. By "chain extender", it is meant a compound having two isocyanate-reactive groups per molecule and a molecular weight of up to about 500, preferably up to about 200. Suitable isocyanate-reactive groups include hydroxyl, thiol, primary amine and secondary amine groups, with hydroxyl, primary and secondary amine groups being preferred and hydroxyl groups being particularly preferred.

Preferred TPUs are rigid, having a glass transition temperature (T_g) of at least 50°C and a hard segment content (defined as the proportion of the weight of the TPU that is made up of chain extender and polyisocyanate residues) of at least 75 percent. Rigid thermoplastic polyurethanes are commercially available under the trade name ISOPLAST® engineering thermoplastic polyurethanes. ISOPLAST is a registered trademark of The Dow Chemical Company.

"Soft" polyurethanes having a T_g of 25°C or less can be used, but tend to form a more flexible composite. Thus, "soft" polyurethanes are preferably used as a blend with a rigid thermoplastic polyurethane. The "soft" polyurethane is generally used in a proportion sufficient to increase the elongation of the composite (in the direction of the orientation of the fibers). This purpose is generally achieved when the "soft" polyurethane constitutes 50 percent or less by weight of the blend, preferably 25 percent or less.

The preferred DRTP can be blended with minor amounts (i.e., 50 percent by weight or less) of other thermoplastics, such as polystyrene, polyvinyl chloride, ethylene vinyl acetate, ethylene vinyl alcohol, polybutylene terephthalate, polyethylene terephthalate, acrylonitrile-styrene-acrylic, ABS (acrylonitrile-butadiene-styrene), polycarbonate, polypropylene and aramid resins. If necessary, compatibilizers can be included in the blend to prevent the polymers from phase separating.

The small cross-section composite of this invention is conveniently prepared by pultruding a thin sheet of composite and, in a subsequent step, cutting the sheet in the direction of the fibers to the desired width to form small cross-section strips. These strips are then cut to the desired length. Of course, the order of cutting can be reversed. The preferred curvature can be imparted to the small cross-section composite on-line, preferably before cutting the sheet down. Less preferably, this can be done in a subsequent operation.

To introduce curves, the impregnated fiber bundle exiting the consolidation unit is conveniently fed through a subsequent moving die that forms a curved or crimped form into the part. A caterpillar-type die having matched dies the act on the profile to form the curves, as described in U. S. Patent No. 5,798,067 to Long, is suitable. Alternatively, a pair of oscillating matched dies can be used to produce a similarly curved profile. Because the matrix resin is a thermoplastic, the introduction of curves using either of these methods can also be done off-line, i.e., separate from the pultrusion process.

Curves or bends of the type illustrated in Figure 2 can also be introduced in a post-forming process, by reheating the composite to a temperature at which the DRTP softens, forming the softened composite into the desired shape, and then cooling.

Again, this is preferably done before the sheet is cut down.

The small cross-section composite of the invention is conveniently used in the same manner as are conventional steel or polypropylene fibers. The small cross-section composite is blended into the wet concrete, either before or after the dry cement or mortar is mixed with water, and mixed to disperse the small cross-section composite throughout the mix. As used herein, "concrete" is used in the usual sense of meaning a mixture of a particulate filler such as gravel, pebbles, sand, stone, slag or cinders in either mortar or cement. Suitable cements include hydraulic cements such as Portland

5 cement, aluminous cement, and the like. The cement or concrete may contain other ingredients such as, for example, plastic latex, hydration aids, curatives, and the like. In addition to the small cross-section composite, other fibers can be included, such as polymeric one-component fibers, bi-component fibers, carbon fibers, ceramic fibers, glass fibers and wood fibers.

10 The concrete containing the dispersed small cross-section composite is then shaped in any convenient manner (such as pouring or the so-called shotcrete process) and allowed to cure to form the concrete structure. A large variety of concrete structures can be made in accordance with the invention, including road surfaces, aircraft runways, walls, building walls and floors, foundations, retaining walls, culverts, tunnels, pillars, and the like. Of course, the small cross-section composite of the invention can be used in conjunction with other types of reinforcements, such as rebars, overwraps and the like.

15 The small cross-section composite will generally constitute up to 10 volume percent of the concrete mixture, preferably from about 0.1 to about 10 volume percent and more preferably from about 0.5 to 2 volume-percent.

20 The resulting concrete structure contains the small cross-section composite embedded within the concrete. The individual pieces of small cross-section composite are advantageously oriented randomly within the concrete, thereby producing omnidirectional reinforcement. In addition, the small cross-section composite helps to hold the wet concrete in place until it has had time to cure, in much the same way as conventional fibers do.

25 The preferred TPU matrix provides the further advantage of adhering well to the concrete, thus increasing effectiveness of the small cross-section composite. Moreover, in the preferred embodiments where the small cross-section composite is adapted to mechanically bond to the concrete, even greater effectiveness is achieved.

30 An important aspect of the invention is that it permits the use of glass fibers as reinforcing materials for concrete. The thermoplastic matrix of the small cross-section composite helps overcome the problem of brittleness that is associated with plain glass fibers. This permits the small cross-section composite to withstand the mixing and pouring processes without significant breakage. In addition, it is believed that the

thermoplastic resin matrix isolates the glass from the alkaline environment of the cement, slowing or preventing the chemical deterioration of the glass.

CLAIMS:

1. A composite adapted for use in a concrete structure, the composite comprising a plurality of longitudinally oriented fibers embedded in a matrix of a depolymerizable and repolymerizable thermoplastic resin, said composite having a longest cross-sectional dimension of not more than 5 mm and an aspect ratio of at least 10.
2. The composite of claim 1, wherein said depolymerizable and repolymerizable thermoplastic includes a thermoplastic polyurethane having a T_g of not less than 50°C.
3. The composite of either of claims 1 or 2, wherein said fibers are glass, other ceramic, carbon, metal or polymeric fibers.
4. The composite of any of claims 1-3, which has a longest cross-sectional dimension of 1 to 3 mm and an aspect ratio of at least about 25.
5. The composite of any of claims 1-4, which has an aspect ratio of at least 40 and a length of 25 to 75 mm.
6. The composite of any of claims 1-5, in which said depolymerizable and repolymerizable polyurethane is blended with a minor amount of a polystyrene, polyvinyl chloride, ethylene vinyl acetate, ethylene vinyl alcohol, polybutylene terephthalate, polyethylene terephthalate, acrylonitrile-styrene-acrylic, ABS (acrylonitrile-butadiene-styrene), polycarbonate, polypropylene or aramid resin.
7. A concrete structure reinforced with up to 10 volume-percent of a small cross-section composite, said small cross-section composite comprising a plurality of longitudinally oriented fibers embedded in a matrix of a depolymerizable and repolymerizable thermoplastic resin, said small cross-section composite having a

longest cross-sectional dimension of not more than about 5 mm and an aspect ratio of at least 10.

8. The concrete structure of claim 8, wherein said depolymerizable and repolymerizable thermoplastic includes a thermoplastic polyurethane having a T_g of not less than 50°C wherein said fibers are glass, other ceramic, carbon, metal or polymeric fibers.
9. The concrete structure of either of claims 8 or 9 which further includes at least one dispersed fiber.
10. The concrete structure of either of claims 9 or 10, in which said depolymerizable and repolymerizable polyurethane is blended with a minor amount of a polystyrene, polyvinyl chloride, ethylene vinyl acetate, ethylene vinyl alcohol, polybutylene terephthalate, polyethylene terephthalate, acrylonitrile-styrene-acrylic, ABS (acrylonitrile-butadiene-styrene), polycarbonate, polypropylene or aramid resin.
11. A method of making a reinforced concrete structure, comprising the steps of (a) forming a wet concrete mix containing a mortar or cement, a particulate filler and up to 10 volume-percent of a small cross-section composite, said small cross-section composite comprising a plurality of longitudinally oriented fibers embedded in a matrix of a depolymerizable and repolymerizable thermoplastic resin, said small cross-section composite having a longest cross-sectional dimension of not more than about 5 mm and an aspect ratio of at least 10, (b) shaping the concrete and (c) permitting the concrete to cure.

1/1




Fig. 1




Fig. 2

BEST AVAILABLE COPY

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/00561

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 E04C5/07

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 E04C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 891 560 A (EDWARDS ET AL.) 6 April 1999 (1999-04-06) cited in the application	1-3,6-11
A	column 2, line 16 -column 7, paragraph 1; figures	4,5
A	US 5 798 067 A (LONG, SR.) 25 August 1998 (1998-08-25) cited in the application	1-11
A	column 3, paragraph 2 -column 4, line 59; figures	
A	US 4 559 262 A (COGSWELL ET AL.) 17 December 1985 (1985-12-17) column 3, line 20 -column 5, line 54; figures	1-11

☐ Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

22 May 2001

Date of mailing of the international search report

30/05/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Righetti, R

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/00561

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5891560	A	06-04-1999	EP 0993487 A WO 9901501 A US 6165604 A	19-04-2000 14-01-1999 26-12-2000
US 5798067	A	25-08-1998	NONE	
US 4559262	A	17-12-1985	AT 25832 T AT 179358 T AU 583374 B AU 554594 B AU 7967782 A DE 3275637 D DE 3280480 D DE 3280480 T DE 875351 T EP 0056703 A EP 0170245 A EP 0875351 A ES 508940 D ES 8307857 A ES 522326 D ES 8407074 A JP 1757342 C JP 57181852 A JP 63037694 B JP 2078561 C JP 3025340 B JP 63239032 A JP 2833694 B JP 8336832 A JP 2569380 B JP 3188131 A JP 2088480 C JP 3243308 A JP 6057407 B NZ 199508 A US 5019450 A US 5213889 A	15-03-1987 15-05-1999 27-04-1989 28-08-1986 29-07-1982 16-04-1987 02-06-1999 11-11-1999 04-11-1999 28-07-1982 05-02-1986 04-11-1998 16-08-1983 01-11-1983 16-08-1984 16-11-1984 20-05-1993 09-11-1982 26-07-1988 09-08-1996 05-04-1991 05-10-1988 09-12-1998 24-12-1996 08-01-1997 16-08-1991 02-09-1996 30-10-1991 03-08-1994 28-02-1985 28-05-1991 25-05-1993